

NV3800

High Viscosity Grey Adhesive vinyl

Description :

Film : 80micron gloss PVC film
Adhesive: High viscosity grey adhesive
Liner : 120gsm one side PEK white silicon paper
Width : 1.06/1.27/1.37/1.52m

Features :

- 1、 Good dimensional stability after application and outdoor durability and performance.
- 2、 Good dimensional stability after application , Easy application to a wide variety of substrates.
- 3、 This glue is permanent viscosity adhesive.

Application :

1. Applicable to Vehicle Wrapping Media, Billboards, indoor and outdoor advertising ; not recommend on cement and brick wall.
2. Suitable for various solvent ink, Eco-solvent ink and UV ink.

Technical data :

Testing condition: Indoor temperature 23±2°C; Relative humidity 50±5%; Use aluminum, glass, steel plate as the base material for testing.

Test Items	units	Test method	Average value
Thickness PVC	Micron	GB/T6672-2001	80±10
Weight-Liner	g/m ²	GB4669-1995	120±10
Weight -finished product	g/m ²	GB4669-1995	255±20
Gloss Rate 60°	%	GB8807-88	≥60
Initial Adhesion	N/25mm	FTM 9	≥10
24h, 180°peel	N/25mm	FTM 1	≥12
Dimensional stability MD	mm	FTM 14	≤2.0
Dimensional stability CD	mm	FTM 14	≤1.8
Tensile strength MD	N/25 mm	GB/T1040.1-2006	≥35
Tensile strength CD	N/25 mm	GB/T1040.1-2006	≥25
Construction Temperature	°C		20±10°C
Applicable Temperature	°C		-20~+70

All technical data is subject to change without prior notice

Storage condition :

All NAR products always need to be stored in the original packing and with the original protection materials, preferably stored hermetically, no more than 6 layers if stored horizontally. Do not expose in direct sunlight or heat sources. Shelf life will be one year with temperature of 25°C±5°C and relative humidity of 50±15%.

Production and Application Environment :

Production environment: temperature of 25±5°C, relative humidity of 50%±10%, clean dust-free environment without suspended matter; please move the materials to the printing environment 24 hours before printing. Test prior to use and remain enough edge margins when printing.

Application environment: temperature of 20±10°C, relative humidity of 50±10%; Pasting on flat, smooth and clean surface without floating dust and shedding; It is necessary to take more than 2 hours for maintenance before laminating.

Warranty Condition :

1. One year shelf life: Stored in suitable conditions, preferably use within six months.
2. One year prosecution period: from the product manufacture date, no-acceptance for overdue product.

Important remark :

1. The information mentioned in this product data sheet is based upon tests that were executed by NAR, and that we consider to be reliable. Environment humidity more than 70% in different district will decrease the printing result.
2. This product is a high viscosity car sticker, which can be used for rough, non-smooth and non-polar stickers. If it is used on outdoor walls, it is recommended to evaluate the adhesive property first.

Product Application :



NAR
IDEAS FOR SIGN