

NO3310TF

Fully compatible three-layer one way vision

Description:

Film: 140micron; black & white PVC film
Adhesive: transparent adhesive
Liner: 75gsm white PEK paper with one side PE & Silicon coating+ 70gsm PEK paper
Width: 1.06/1.27/1.37/1.52m

Features:

1. One side visual, sun-shade and privacy protection; Hole size 1.60mm, perforation 40%;
2. Stable ink absorption and excellent dimensional stability;
3. Three-layer fit, suitable for a variety of model spray painting.

Applications:

1. Applicable to glass surface, also applicable to transparent acrylic, PVC, PET transparent panels;
2. Suitable for various of solvent ink, Eco-solvent, UV& HP-Latex ink.

Technical Data:

Testing condition: Indoor temperature 23±2°C; Relative humidity 50±5%; Use aluminum, glass, steel plate as the base material for testing.

Test Items	Units	Test method	Average value
Thickness PVC	Micron	GB/T6672-2001	140±10
Weight-Liner	g/m ²	GB4669-1995	135±10
Weight -finished product	g/m ²	GB4669-1995	270±20
24h, 180° peel	N/25mm	FTM 1	≥4
Dimensional stability MD	mm	FTM 14	≤1.5
Dimensional stability CD	mm	FTM 14	≤1.0
Tensile strength MD	N/25 mm	GB/T1040.1-2006	≥25
Tensile strength CD	N/25 mm	GB/T1040.1-2006	≥20
Construction Temperature	°C		20±10
Applicable Temperature	°C		-20 ~ +70

* All technical data is subject to change without prior notice.

Storage Condition:

All NAR products always need to be stored in the original packing and with the original protection materials, preferably stored hermetically, no more than 6 layers if stored horizontally. Do not expose in direct sunlight or heat sources. Shelf life will be one year with temperature of 25°C±5°C and relative humidity of 50±15%.

Production and Application Environment:

Production environment: temperature of 25±5°C, relative humidity of 50%±10%, clean dust-free environment without suspended matter; Please move the materials to the printing environment 24 hours before printing. Test prior to use and remain enough edge margins when printing.

Application environment: temperature of 20±10°C, relative humidity of 50±10%; Pasting on flat, smooth and clean surface without floating dust and shedding; It is necessary to take more than 2 hours for maintenance before laminating.

Warranty Condition:

1. One year shelf life: stored in suitable conditions, preferably use within 6 months;
2. One year prosecution period: from the product manufacture date, no-acceptance for overdue product.

Important Remarks:

1. The information mentioned in this product data sheet is based upon tests that were executed by NAR, and that we consider to be reliable. Environment humidity more than 70% in different district will decrease the printing result.

Product Application:



NAR
IDEAS FOR SIGN